Professional Testing Laboratory, Inc.

TEST REPORT

DATE: 09/30/2013 **TEST NUMBER**: 160674

CLIENT	LG Hausys America, Inc. (GA)

TEST METHOD CONDUCTED	ASTM F2199-09 Test Method for Determining Dimensional Stability of Resilient Floor Tile after Exposure to Heat

	DESCRIPTION OF TEST SAMPLE
IDENTIFICATION	Uncommon Ground/Crete/Jeogori
COLOR	-----
ROLL	-----
CONSTRUCTION	LVT
FIBER	-----
BACKING	-----
REFERENCE	

GENERAL PRINCIPLE

This test method is intended for use in determining the linear change of resilient flooring after being exposed to heat. The largest dimensional change is reported as the dimensional stability.

TEST RESULTS

IDENTIFICATION	RESULT
Length	-0.006 Inch per 12 inches (0.05% Loss)
Width	-0.004 Inch per 12 inches (0.03% Loss)

APPROVED BY: Gary Ashury

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us