Professional Testing Laboratory, Inc.

TEST REPORT

DATE: 09/30/2013 **TEST NUMBER**: 160674

CLIENT	LG Hausys America, Inc. (GA)

TEST METHOD CONDUCTED	ASTM F410-08 Standard Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

	DESCRIPTION OF TEST SAMPLE
IDENTIFICATION	Uncommon Ground/Crete/Jeogori
COLOR	-----
ROLL	-----
CONSTRUCTION	LVT
FIBER	-----
BACKING	-----
REFERENCE	

GENERAL PRINCIPLE

The thickness of the wear layer of resilient non-textile floor coverings is determined by microscopic optical measurement. The specimen is examined in three areas and measurements are made on the outer most layer of the composite material. The measurements are recorded to the .001 inch and averaged.

TEST RESULTS

	THICKNESS	
SPECIMEN 1	0.0220 inch	0.55 mm
SPECIMEN 2	0.0210 inch	0.54 mm
SPECIMEN 3	0.0190 inch	0.49 mm

AVERAGE TOTAL THICKNESS	0.0207 Inch	0.53 mm

APPROVED BY: Gary Ashury

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us