Professional Testing Laboratory, Inc.

TEST REPORT

DATE: 09/30/2013 **TEST NUMBER**: 160674

CLIENT	LG Hausys America, Inc. (GA)

TEST METHOD CONDUCTED	ASTM F925-02 5 Minute Standard Test Method for Resistance to Chemicals of Resilient Flooring

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Uncommon Ground/Crete/Jeogori
COLOR	-----
ROLL	-----
CONSTRUCTION	LVT
FIBER	-----
BACKING	-----
REFERENCE	

TEST RESULTS

5 MINUTE RATINGS

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0
70% Isopropyl Alcohol	0	0	0
Mineral Oil	0	0	0
5% Sodium Hydroxide	0	0	0
5% Hydrochloric Acid	0	0	0
5% Ammonia	0	0	0
Bleach	0	0	0
5% Phenol	0	0	0
Gasoline	0	0	0
Sulfuric Acid	0	0	0
Kerosene	0	0	0
Olive Oil	0	0	0

RATING KEY
0 - No change (----)
1 - Slight change
2 - Moderate change
3 - Severe change

APPROVED BY: Gary Ashbury

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us