



Material Engineering Laboratory-Taichung



Testing Laboratory
0292

TEST REPORT



Report NO. : TB-15-05758ZA

C-15-18879

Page NO. : 1 OF 1

Date : Oct. 22,2015

Project Name : Self Evaluation
 Contractor : -----
 Applicant : LG Hausys Taipei Office
 Supplier : -----
 Sample Name : Interior Film
 Sample Submitted By : LG Hausys Taipei Office
 Date of Sample Received : Oct. 14,2015
 Date of Testing : Oct. 14,2015 ~ Oct. 22,2015
 Remark : The information mentioned in the above section is provided by Client
 (Exclude Date of Sample Received and Date of Testing)

Test Results :

Test Item	Test Result	Standard values of CNS 7614(1994) Anti-flaming Grade 1	Standard values of CNS 7614(1994) Anti-flaming Grade 2	Standard values of CNS 7614(1994) Anti-flaming Grade 3	Test Method
Flames heating time(sec)	10	-----	-----	-----	CNS 7614(1994) A Method
Remaining flame time (sec)	0.0	≤ 1	≤ 5	≤ 5	
Embers time (sec)	0.0	≤ 60	≤ 60	≤ 60	
Length of carbonization (cm)	4.7	≤ 5	≤ 10	≤ 15	

Note1 : Sample thickness is 3.5 mm.


Note2 : Test performed by Sammy Chou.

Note3 : The sample is used Interior Film to paste on the wood.

Note4 : This test report is an additional original report of TB-15-05758Z C-15-18879. Issued date : Oct. 22,2015.

----- oOo -----

The required specification(s) offered in this test report is/are for reference only.
The conformity judgment is at the Applicant's final verdict.


 Signed for and on behalf of
SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



Material Engineering Laboratory-Taichung



Testing Laboratory
0292

TEST REPORT



Report NO. : TB-15-05758ZA
C-15-18879
Page NO. : 1 OF 1
Date : Oct. 22,2015

Project Name : Self Evaluation
 Contractor : -----
 Applicant : LG Hausys Taipei Office
 Supplier : -----
 Sample Name : Interior Film
 Sample Submitted By : LG Hausys Taipei Office
 Date of Sample Received : Oct. 14,2015
 Date of Testing : Oct. 14,2015 ~ Oct. 22,2015
 Remark : The information mentioned in the above section is provided by Client
 (Exclude Date of Sample Received and Date of Testing)

Test Results :

Test Item	Test Result	Standard values of CNS 7614(1994) Anti-flaming Grade 1	Standard values of CNS 7614(1994) Anti-flaming Grade 2	Standard values of CNS 7614(1994) Anti-flaming Grade 3	Test Method
Flames heating time(sec)	10	-----	-----	-----	CNS 7614(1994) A Method
Remaining flame time (sec)	0.0	≤ 1	≤ 5	≤ 5	
Embers time (sec)	0.0	≤ 60	≤ 60	≤ 60	
Length of carbonization (cm)	4.7	≤ 5	≤ 10	≤ 15	

Note1 : Sample thickness is 3.5 mm.


Note2 : Test performed by Sammy Chou.

Note3 : The sample is used Interior Film to paste on the wood.

Note4 : This test report is an additional original report of TB-15-05758Z C-15-18879. Issued date : Oct. 22,2015.

-----oOo-----

The required specification(s) offered in this test report is/are for reference only.
The conformity judgment is at the Applicant's final verdict.



Signed for and on behalf of
SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.