

CDM ESD 68910N

- **New generation material with higher performances in temperature at 300-350°C**
- **Excellent flux and chemical resistance**
- **Very good machinability especially on thin wall machining down to 0,5-0,7mm**
- **Excellent dimensional stability with very good mechanical characteristics**
- **Dissipative material**
- **Thin wall capability**

Description

CDM ESD 68910N is a composite material based on glass mat reinforcement in combination with dissipative, high temperature and high corrosion resistant resin system. CDM ESD 68910N is a new generation material taking into account the necessity of thin walls machining.

Electrostatic discharge damage electronic components and circuits every day. To use CDM will allow charges to move slowly out of the circuit and will ensure the quality of your production. CDM ESD product have guaranteed dissipative characteristics.

The CDM range of products exhibits higher mechanical and resistance properties as standard composite materials.

The random glass mat substrate present in the CDM ESD 68910N minimizes delamination problems during machining or pallet use.

The relative low thermal conductivity in the CDM materials allows quick pallet turnaround eliminating most of the time both the necessity to provide a cooling station and the process heat sink effect experienced in the metallic pallets. CDM materials can substitute metallic solder frames with great advantages.

Flux resistance is depending on composition and pH level. CDM has been developed to have a better withstand towards chemicals. To preserve the stability of CDM material, a regular cleaning can still be made. Due to the high fiberglass content, machining is recommended with carbide or diamond toolings. Precise machining with very accurate tolerances can be achieved by experts in the conception and machining of pallets.

Application

- Full process solder wave, SMT selective soldering process
- Components insertion
- Silk screen printing of solder paste in SMT
- SMT placement
- Reflow soldering
- Components protection
- Testing of PCBs

Availability

Standard thicknesses available: 3mm, 4mm, 5mm, 6 mm, 8 mm, 10mm, 12mm (other thicknesses available)

Standard sheet size for 3mm and 4mm: 1335 ±10mm x 1170 ±10mm

Standard sheet size for 5mm to 12mm: 2350 ±10mm x 1335 ±10mm

Thickness tolerance: ±0,10mm for 3mm to 10mm and ± 0,15mm for 12mm

Flatness (panel size 300x300mm): 0,2mm

Surface quality: sanded on both sides

Colour
Black

Technical recommendations

When in contact with aggressive chemicals, cleaning of pallets on a regular basis is recommended in order to maximize the effective life span of the CDM pallets.

Storage: on flat and plane pallet in sane and dry warehouse. Avoid contact of CDM material to atmospheric influences such as UV, rain, high humidity rates.

PVC packaging around the sheets and panels is preferable in case of humidity environment.

Physical Properties	Unit	Value	Test Method
Density	g/cm ³	1,9 ±0,1	ISO 1183 (Method A)
Water absorption (24h 23°C)	%	< 0,15	ISO 62 (Method 1)
Linear coefficient of thermal expansion, parallel	K ⁻¹	10.10 ^{E-6}	TMA

Electrical Properties	Unit	Value	Test Method
Surface resistance (R _s)	Ω	1x10 ⁴ ≤ R _s < 1x10 ⁷	IEC 61340-2-3 (*)
Volume resistance (R _v)	Ω	1x10 ⁴ ≤ R _v < 1x10 ⁸	IEC 61340-2-3 (**)

Mechanical Properties	Unit	Value	Test Method
Flexural strength at 23°C, flatwise	MPa	380	ISO 178
Flexural strength at 150°C, flatwise	MPa	250	ISO 178
Flexural strength at 200°C, flatwise	MPa	120	ISO 178
Modulus of elasticity in flexure at 23°C, flatwise	MPa	18 000	ISO 178
Modulus of elasticity in flexure at 150°C, flatwise	MPa	13 000	ISO 178
Modulus of elasticity in flexure at 200°C, flatwise	MPa	8 000	ISO 178

(*) values also granted for ASTM D257 and STM 11.11

(**) values also granted for ASTM D257 and STM 11.12

The product properties set forth in this data sheet are based on the results of testing of typical material produced by Isola Composite France SA. Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Isola Composite France SA does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Isola Composite France SA expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Isola Composite France SA makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Isola Composite France SA shall in no event be liable for incidental, exemplary, punitive or consequential damages.